

Amendments to the Claims:

1. (Currently Amended) A method of forming an interconnect in a substrate which includes one or more dielectric layers and a copper deposit, said method comprising: forming a trench in the substrate; forming a via in the substrate to the copper deposit; depositing an interconnect liner layer of ~~aluminum-copper alloy comprised primarily of Aluminum~~ aluminum-0.5% copper alloy in the trench and via; depositing copper onto the ~~aluminum-copper~~ aluminum-0.5% copper alloy interconnect liner layer; and polishing the copper, wherein the interconnect liner layer is a permanent component of the interconnect and does not interact with the copper or copper deposit to form an alloy at any time while the method is performed.

2. (Currently Amended) A method as recited in claim 1, wherein the step of depositing a layer of ~~aluminum-copper alloy comprises depositing aluminum-0.5% copper alloy~~ comprises using a PVD technique.

3. (Currently Amended) A method of forming an interconnect in a substrate which includes one or more dielectric layers and a copper deposit, said method comprising: forming a trench in the substrate; forming a via in the substrate to the copper deposit; depositing an intermediate liner layer in the trench and via and on the copper deposit; depositing an interconnect liner layer of ~~aluminum-copper alloy comprised primarily of Aluminum~~ aluminum-0.5% copper alloy on the intermediate layer; depositing copper onto the ~~aluminum-copper~~ aluminum-0.5% copper alloy; and polishing the copper, wherein the interconnect liner layer is a

Serial No.: 10/615,042
Art Unit: 2815
Page 2

permanent component of the interconnect and does not interact with the copper or copper deposit to form an alloy at any time while the method is performed.

4. (Currently Amended) A method as recited in claim 3, wherein the step of depositing a layer of ~~aluminum-copper alloy comprises depositing~~ aluminum-0.5% copper alloy ~~comprises~~ using a PVD technique.

5. (Original) A method as recited in claim 3, wherein the step of depositing an intermediate liner layer comprises depositing Ta/TaN.

6. (Currently Amended) An interconnect in a substrate which includes one or more dielectric layers, said interconnect comprising a first copper deposit, a second copper deposit, and an ~~aluminum-copper~~ aluminum-0.5% copper alloy interconnect liner ~~comprised primarily of~~ ~~Aluminum~~ and disposed between and in contact with the first and second copper deposits and between the second copper deposit and at least one of the dielectric layers, wherein the interconnect liner is a permanent component of the interconnect and is not combined with either of the copper deposits to form an alloy.

7. (Previously Presented) An interconnect as recited in claim 6, wherein the aluminum-copper alloy interconnect liner has been deposited using a PVD technique.

Serial No.: 10/615,042
Art Unit: 2815
Page 3

FROM TREXLER ETAL.

(FRI) 4. 29' 05 11:52/ST. 11:50/NO. 4860347881 P 7

8-14. (Cancelled)

Serial No.: 10/615,042

Art Unit: 2815

Page 4